



TECHNICAL DATA SHEET

SUPER LUBE® SILICONE LUBRICATING GREASE WITH SYNOLON® (PTFE) March 2017

PRODUCT DESCRIPTION:

Super Lube® Silicone Lubricating Grease with Synolon® (PTFE) is a non-curing silicone compound ideal for sealing, protecting and insulating electrical components and connectors. The addition of Synolon® (PTFE) micro powders combine to form a premium lubricant that provides longer life protection against friction, wear, rust and corrosion.

Super Lube® Silicone Lubricating Grease with Synolon® (PTFE) is waterproof and protects against moisture and other contaminants in electrical connections.

Super Lube® Grease is a NSF registered Food Grade lubricant, rated H1 for incidental food contact. Meets former USDA (H1) guidelines.

Super Lube® Silicone Lubricating Grease with Synolon® (PTFE) is translucent white, clean and clear in appearance and exhibits high dielectric strength and is compatible with most plastics and rubbers. It will not harden, dry out or melt.



FEATURES:

- ❖ Vacuum grease
- ❖ High dielectric strength
- ❖ Prevents rust and corrosion
- ❖ Food grade and clean
- ❖ Excellent heat transfer efficiency
- ❖ Viscosity stable
- ❖ Thermally stable
- ❖ Wide temperature range
- ❖ Compatible with majority of rubber and plastic compounds
- ❖ Seals out moisture
- ❖ Heavy consistency
- ❖ Environmentally friendly
- ❖ NSF Registered (H1), #141974
- ❖ Kosher certified

TYPICAL APPLICATIONS:

- ❖ O-rings
- ❖ Faucet valves
- ❖ Rubber gaskets
- ❖ Window channels
- ❖ Electrical connectors
- ❖ Food processing equipment
- ❖ Vacuum/Chamber sealant
- ❖ Calipers

PACKAGE SIZES:

Part No.	Description
92000	1 cc. Packet
92003	3 oz. Tube
92150	400 gram Cartridge
92016	400 gram Canister
92005	5 lb. Pail
92030	30 lb. Pail
92400	400 lb. Drum



TECHNICAL DATA SHEET

SUPER LUBE® SILICONE LUBRICATING GREASE WITH SYNOLON® (PTFE) March 2017

PROPERTIES:

Test	Test Method	Rating
Color:		Translucent white
Temperature Range:		-40°F to 500°F (-40°C to 260°C)
Penetration, Worked 60 strokes:	ASTM D217	265 - 295
Oil Separation, 21 hrs. / 100°C:	ASTM D6184	< 3%
Melting Point:		No Melt
Specific gravity @ 25°C (77°F)	ASTM D1298	0.90
Water washout:	ASTM D1264	< 1.0%
Load wear index: Last non-seizure load (scar)(psi)	ASTM D2783	24.49 kgf 16 kg (0.28 mm) (150,811 psi)
Last seizure load (scar) (psi)		126 kg (1.60 mm) (36,388 psi)
Weld load		160 kg
NLGI		2

DIRECTIONS:

- Clean and dry area to be treated.
- Apply with a clean cloth, brush, sponge or finger.
- Remove excess.

SHELF LIFE / WARRANTY:

Super Lube® products have a five (5) year recommended shelf life when stored in the original container and in reasonable ambient conditions. The warranty period is twenty-four (24) months from the date of purchase. For complete information visit [www.super-lube.com/what-is-the-shelf-life-ezp-320.html](http://www.super-lube.com/what-is-the-shelf-life-ezp-320.html).



See Safety Data Sheet (SDS) for further details regarding safe use of this product.



Made in USA

The information provided in this Technical Data Sheet including the recommendations for use and application of the product are based on our knowledge and experience of the product as of the date of this bulletin. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Synco Chemical Corporation is, therefore not liable for the suitability of our product for the production processes and conditions in respect for which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

All Super Lube® and Synolon® trademarks in this document are trademarks of Synco Chemical Corporation.