

Super Lube® "...everywhere and no wear"!



SYNCO CHEMICAL CORPORATION

24 DaVinci Drive, PO Box 405

Bohemia, NY 11716-0405

Phone (631) 567-5300, Fax (631) 567-5359

e-mail: info@super-lube.com

www.super-lube.com



COMPATIBILITY CHART

Multi-Purpose Synthetic Lubricant with Synolon® (PTFE)

Polymer (plastics) Constant Strain Tensile Testing	Rating
Acrylonitrile Butadiene Styrene (ABS)	E
Cellulose acetate (CA)	E
Polyamide (PA) (Nylon)	E
Polycarbonate (PC)	G
Polyethylene (PE)	E
*ultra high molecular mass (PE-UHMW)	E
*low density (PE-LD)	E
Polyethylene/polybutylenetherephthalat (PET / PBT)	E
Polyoxymethylene, Polyacetate (POM) (Delrin)	E
Polypropylene (PP)	E
Polyphenylene oxide (PPO)	E
Polyphenylene sulphide (PPS)	E
Polystyrene (PS)	G
Polytetrafluoroethylene (PTFE)	E
Polyurethane (PUR)	E
Polyvinylchloride (PVC)	E
Thermoplastic elastomer (TPE)	E
Elastomer (rubber)	Rating
Acrylic rubber (ACM)	E
Buna S	NC
Butyl (IIR)	NC
Polychloroprene rubber (CR)	G
Chlorosulphonated PE-rubber (CSM)	E
Ethylene-propylene-diene rubber (EPDM)	NC
Fluorinated rubber (FKM)	E
Natural rubber (NR)	NC
Neoprene	E
Nitrile (NBR)	E
Polyurethane (AU, EU)	E
Propylene-tetrafluoroethylene rubber (FPM, FEPM)	E
Styrene-butadiene rubber (SBR)	NC
Silicone rubber (FMQ, PMQ, MQ, VMFQ, VMQ)	G
Viton (FKM)	E
RATING KEY	
E - Compatibility Excellent	
G - Compatibility Good	
NC - Not Compatible	