



TECHNICAL DATA SHEET

SUPER LUBE® SILICONE DIELECTRIC GREASE

April 2018

PRODUCT DESCRIPTION:

Super Lube® Silicone Dielectric Grease is a non-curing silicone compound ideal for sealing, protecting and insulating electrical components and connectors. It is waterproof and protects against moisture and other contaminants in electrical connections.

Super Lube® Silicone Dielectric Grease is a NSF registered Food Grade lubricant, rated H1 for incidental food contact. Meets former USDA (H1) guidelines.

Super Lube® Silicone Dielectric Grease is translucent white, clean and clear in appearance and exhibits high dielectric strength. It is compatible with most plastics and rubbers.



FEATURES:

- ❖ Vacuum grease
- ❖ High dielectric strength
- ❖ Food grade and clean
- ❖ Seals out moisture
- ❖ Lubricates rubbers and plastics
- ❖ Heavy consistency
- ❖ Protects electrical components from corrosion
- ❖ Prevents electrical arcing
- ❖ Wide temperature range
- ❖ Compatible with majority of rubber and plastic compounds.
- ❖ Environmentally friendly
- ❖ Biodegradable
- ❖ Kosher certified
- ❖ NSF Registered (H1), #141973

TYPICAL APPLICATIONS:

- ❖ Electrical insulation, damping and lubrication of brass components and O-rings.
- ❖ Protects battery cables, spark plugs and distributor caps.
- ❖ Cable connections
- ❖ Terminal strips and disconnects
- ❖ Vacuum/Chamber Sealant
- ❖ Food processing equipment
- ❖ Lubricates and moisture proofs

PACKAGE SIZES:

Part No.	Description	Part No.	Description
91003	3 oz. Tube	91400	400 lb. Drum
91015	400 gram Cartridge	91015/UV*	400 gram Cartridge
91016	400 gram Canister	91016/UV*	400 gram Canister
91005	5 lb. Pail	91005/UV*	5 lb. Pail
91030	30 lb. Pail	91030/UV*	30 lb. Pail
91120	120 lb. Keg		

*UV tracer added validates the existence of the lubricant.



TECHNICAL DATA SHEET

SUPER LUBE® SILICONE DIELECTRIC GREASE

April 2018

PROPERTIES:

Test	Test Method	Rating
NLGI Grade:	ASTM D1092	2
Color:		Translucent white
Temperature Range:		-40°F to 500°F (-40°C to 260°C)
Viscosity (Base Oil) cSt @ 25°C:	ASTM D445	5000
Specific Gravity @ 25°C (77°F):	ASTM D1298	0.90
Penetration, Worked 60 strokes:	ASTM D217	265 – 295
Vapor Pressure @ 200°C (Pascal):		1.33
Specific Heat (Joules/g,°C)		1.5
Thermal Conductivity (Watt/m.°C):		0.16
Dielectric Strength (Volts/mil, 50 mil gap):	CTM 0114	400
Dielectric Loss:	ASTM D924	1.2 x 10 ¹²
Dielectric Resistivity @ 25°C (ohm/cm):	ASTM D1169	1 x 10 ¹⁵
Dielectric Constant @25°C between 0.5 and 100 kHz:	ASTM D924	2.8
Oil Separation, 21 hrs. / 100°C:	ASTM D6184	<1%
Evaporation Loss 22 hrs. @ 212°F (100°C)	ASTM D972	< 1%
Flash Point:	ASTM D92	>572°F (300°C)
Melting Point:		No Melt
Water Washout:	ASTM D1264	< 1%
Biodegradability:	CEC-L33-T82	50% degradability in 28-35 days 60+% degradability in 56 days

DIRECTIONS:

- Clean mating surfaces.
- Apply evenly to surfaces.



TECHNICAL DATA SHEET

SUPER LUBE® SILICONE DIELECTRIC GREASE

April 2018

SHELF LIFE / WARRANTY:

Super Lube® products have a five (5) year recommended shelf life when stored in the original container and in reasonable ambient conditions. The warranty period is twenty-four (24) months from the date of purchase. For complete information visit www.super-lube.com/what-is-the-shelf-life-ezp-320.html.



See Safety Data Sheet (SDS) for further details regarding safe use of this product.



Made in USA

The information provided in this Technical Data Sheet including the recommendations for use and application of the product are based on our knowledge and experience of the product as of the date of this bulletin. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Synco Chemical Corporation is, therefore not liable for the suitability of our product for the production processes and conditions in respect for which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

All Super Lube® trademarks in this document are trademarks of Synco Chemical Corporation.

